



NOTES:

1. FOR PROJECTS USING 90-MIL MEMBRANE, ALL INSIDE CORNERS MUST BE COMPLETED WITH TWO LAYERS OF PEEL & STICK FLASHING. THE BOTTOM LAYER SHALL BE A PEEL & STICK PRE-CUT T-JOINT COVER OR A 6"X6" (152mm X 152mm) PEEL & STICK UNCURED EPDM FLASHING PIECE COVERED WITH A 12"X12" (305mm X 305mm) TOP LAYER OF PEEL & STICK UNCURED EPDM FLASHING. BOTH LAYERS SHALL BE CENTERED AND SEALED WITH CONTINUOUS LAP SEALANT.
2. EPDM PRIMER MUST BE APPLIED TO ALL SPLICE AREAS AND FOR EACH LAYER OF PEEL & STICK FLASHING.



INSIDE CORNER WITH CONTINUOUS EPDM WALL FLASHING

—• EPDM MEMBRANE

—• APPROVED SUBSTRATE

0 —• SEE NOTE

EPDM ROOFING SYSTEM

WBRC-15.3