



NOTES:

1. OVERLAPPED FIELD APPLIED PAS SEAM TAPE A MINIMUM OF 1" (2.5cm). APPLY LAP SEALANT AT TAPE OVERLAPS 2" (5cm) IN EACH DIRECTION AS SHOWN.
2. APPLY LAP SEALANT ALONG THE LEADING EDGE OF THE MEMBRANE SPLICE UNDER THE 6"x6" (15cm X 15cm) T-JOINT COVER, COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN ALL DIRECTIONS FROM THE SPLICE INTERSECTION.
3. WHEN USING 90-MIL MEMBRANE, INSTALL A 12" (30cm) T-JOINT COVER CENTERED OVER THE FIRST T-JOINT COVER PER DETAIL [WBRC-2.2](#)
4. LAP SEALANT IS REQUIRED ON CUT EDGES OF REINFORCED EPDM MEMBRANE.
5. REFER TO DETAIL [WBRMA-2.1](#) FOR MECHANICALLY FASTENED SPLICES.



EPDM MEMBRANE SPLICES

	→ EPDM MEMBRANE
	→ APPROVED SUBSTRATE
	→ SEE NOTE

EPDM ROOFING SYSTEM

WBRC-2.1A