

WeatherBond

Type VI Glass Ply Felt



Overview

WeatherBond's Type VI Glass Ply Felt is manufactured with a heavyweight fiberglass mat containing heat-cured resinous binders for added dimensional stability. The high strength glass mat is saturated with type IV asphalt, giving our type VI felt excellent breaking strength, as well as a uniform porosity for ease in applications.

WeatherBond's Type VI meets ASTM D-2178 Type VI felt and may be used as an inner ply or base ply in a WeatherBond multi-ply system. It may be used as a base ply when mopped in place over asphalt-compatible substrates. When installed in a two ply format WeatherBond's Type VI Glass Ply Felt may be used as a temporary roof.

Features and Benefits

- Consistent tensile strength and tear resistance
- Low moisture absorption and excellent dimensional stability
- Easy to handle and lays flat
- Non-slip surface
- Meets Underwriters Laboratories (UL) G-2 base sheet requirements

Application

WeatherBond Type VI Glass Ply Felt is used as a base or inner-ply in conjunction with WeatherBond's AFX cap sheets. For non-nailable decks Type VI can be adhered directly to the primed substrate with type III or IV asphalt, SEBS mopping asphalt or WeatherBond's Cold Applied Adhesive. For nailable decks, WeatherBond's G2 Base Sheet is typically mechanically fastened (using WeatherBond approved fasteners) to the substrate as the first ply and subsequent layers of Type VI Glass Ply Felt are mopped to the base ply. Consult WeatherBond specifications for complete installation information.

Specifications

- Width – 36"
- Length – 180'
- Roll Weight – 53 lbs

Typical Properties and Characteristics

ASTM	D 2178-04 Type VI
UL	Type G2
Breaking Strength, lbf/in (kN/m)	
Longitude	60 (10.5)
Transverse	60 (10.5), min
Pliability at 77°F and 50% RH; ½" Radius (pass/fail)	
Longitude	PASS
Transverse	PASS
Net Dry Mass of Saturated Felt, lbs/100 ft. ²	> 6.0
Net Dry Mass of Asphalt-impregnated Glass Felt, lbs/100 ft. ² (g/m ²)	
Average of all rolls	
–nonlinearly parting agent	6.2 (303)
–mineral parting agent	7.0 (342)
Individual rolls	6.0 (293)
Moisture, at the time of manufacturing	1.0%, max
Mass of desaturated glass felt, lbs/100 ft. ²	1.9 (93), min
Asphalt, lbs/100 ft. ² (g/m ²)	3.0 (146), min
Ash	70% to 88%
Parting Agent and Stabilizer, lbs/100 ft. ² (g/m ²)	3.0 (146), max

LEED® Information

Pre-consumer Recycled Content	0%
Post-consumer Recycled Content	0%
Manufacturing Location	Tuscaloosa, AL

Packaging

Product	Type VI Glass Ply Felt
Size	36" x 180' / 45 lbs
Actual Coverage	500 ft ²
Part Number	318312



WEATHERBOND
ROOFING SYSTEMS

Single-Ply Simplified

P.O. Box 251 | Plainfield, PA 17081 | 866.471.5125 | FAX: 717.960.4034 | www.weatherbondroofing.com

© 2019 WeatherBond. 08.12.19
WeatherBond is a trademark of WeatherBond. LEED is a registered trademark of the U.S. Green Building Council.