

# WeatherBond

## CCW-702 and 702LV



### Overview

CCW-702 and 702LV are quick-drying, solvent-based, high-tack adhesives specifically designed to promote maximum adhesion of WeatherBond's VapAir Seal™ 725TR to approved substrates. They are also used as a surface prep to promote adhesion with DASH adhesives. CCW-702 and 702LV are available in 5-gallon pails and packaged 45 pails per pallet.

### Features and Benefits

- Enhances bond of VapAir Seal 725TR
- Can be walked on once cured or flashed off
- Acts as a surface prep to enhance adhesion of DASH adhesives

### Application

Apply by medium nap roller or brush in an even film at 300 to 350 square feet per gallon. Caution must be taken not to apply excess contact adhesive which could cause longer drying times. Allow adhesive to dry for 20 minute maximum at 75°F. Porous substrates like DensDeck® Prime, gypsum decks and lightweight insulating concrete decks require additional material, reducing the coverage rates for proper adhesion. Adhesive has a satisfactory cure when surface is tacky, but will not transfer when touched. Apply only to areas to be waterproofed the same day. Reapply if area becomes dirty or wet. When used in adverse climate conditions (i.e. humid, cool, etc.) or on a porous substrate, additional time will be required.

All fluid-applied product application rates are based on theoretical coverage relative to the percentage of solids in the material. These are minimum application rates to achieve the required dry film thickness for the system and do not account for substrate condition or porosity. A thicker application of the product may be necessary to achieve the required dry film thickness for system relative to the substrate.

NOTE: CCW-702 and 702LV may not be compliant in all Low-VOC states.

REVIEW CURRENT WEATHERBOND INSTALLATION INSTRUCTIONS FOR SPECIFIC APPLICATION REQUIREMENTS.

### Precautions

1. Flammable liquid and vapors. Use only with adequate ventilation and avoid breathing vapors. Refer to SDS for other important warnings and product safety information.
2. Do not apply to damp or frozen substrates.
3. Store at 35°F to 110°F (2° to 43°C).

### LEED® Information

	702	702LV
Pre-consumer Recycled Content	0	0
Post-consumer Recycled Content	0	0
Manufacturing Location	Carlisle, PA	Carlisle, PA

### Typical Properties and Characteristics

Physical Property	702	702LV
Weight Per Gallon	7.5 lbs	7.5 lbs
Solids Content	46% by wt	46% by wt
VOC Content	450 g/L	<250 g/L
Color	Blue	Red
Flash Point	-4°F (-20°C)	-4°F (-20°C)
Adhesion to Concrete	11.0 lb/lin in	11.0 lb/lin in
Minimum Application Temp	25°F (3.9°C)	25°F (3.9°C)
Viscosity	200 cps	200 cps
Storage Temp	35°F to 110°F	35°F to 110°F

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.



**WEATHERBOND**  
ROOFING SYSTEMS

Single-Ply Simplified

P.O. Box 251 | Plainfield, PA 17081 | 866.471.5125 | FAX: 717.960.4034 | [www.weatherbondroofing.com](http://www.weatherbondroofing.com)

© 2017 WeatherBond. 10.25.17  
WeatherBond is a trademark of WeatherBond. VapAir Seal is a trademark of Carlisle Construction Materials, LLC.  
DensDeck is a registered trademark of Georgia-Pacific. LEED is a registered trademark of the U.S. Green Building Council.