

WeatherBond PVC

FRS Fleece Membrane



Overview

WeatherBond FRS PVC Fleece membranes are manufactured using a state-of-the-art extrusion process for complete scrim encapsulation. The PVC is reinforced with a high-strength fiberglass scrim and enhanced with fleece, creating a very tough, durable and versatile sheet that is ideal for re-roofing or new construction projects. Available in total sheet thicknesses of 115- and 135-mils, this product can be used in fully adhered and mechanically attached applications.

WeatherBond's PVC formulation delivers excellent weatherability, flexibility and toughness, and the fiberglass reinforcing scrim provides additional dimensional stability to the sheet. In addition to providing a built-in separation layer for rough concrete decks or existing asphaltic-based roofing systems, the fleece backing enhances the membrane's puncture resistance.

Features and Benefits

- Available in white, gray, and tan
- Available in thicknesses of 115- and 135-mils
- Roll Sizes:
 - 115-mil = 10' x 80'
 - 135-mil = 10' x 65'
- Superior wind uplift resistance due to the bond between fleece and adhesive
- 67% fewer seams than Modified Bitumen systems (using 10'-wide sheets)
- Wide window of weldability
- Fleece reinforcement adds toughness, durability and enhanced puncture resistance
- Fiberglass reinforcing scrim provides excellent breaking strength
- Low-volatility plasticizer



WEATHERBOND
ROOFING SYSTEMS

- Good chemical resistance to acids, bases, restaurant oils, fats, greases and acid rain
- White PVC is California Title 24 compliant and can contribute to LEED® (Leadership in Energy and Environmental Design) credits.

Installation

Mechanically Fastened Roofing System

The mechanically fastened system starts with approved insulation being fastened with a minimum of 5 fasteners per 4' x 8' board. The Fleece PVC FRS membrane is then mechanically fastened to the deck using HPWX Fasteners and HPWX Plates. Adjoining sheets of Fleece PVC membrane are overlapped over the fasteners and plates and joined together with a minimum 1½"-wide hot-air weld.

Adhered Roofing System – Low Rise Foam

Insulation is mechanically attached or adhered with Flexible DASH Adhesive to the roof deck. Spray-apply or extrude adhesive onto the substrate, and allow foam to develop string/body/gel prior to setting Fleece membrane into the adhesive. Roll Fleece membrane with a 30"-wide, 150-pound (68 kg) segmented weighted roller to ensure full embedment. Splices are hot-air welded.

Adhered Roofing System – Water Based

The fully adhered system starts with a suitable surface on which to apply the HydroBond™ Water-Based Adhesive. HydroBond can be applied to the approved substrate with a medium nap roller. Once the adhesive has been applied, roll the membrane in place. To prevent over-drying, WeatherBond recommends applying the adhesive 3' – 4' at a time ahead of the roll. Immediately broom the membrane starting from the center and working out to the sides of the sheet using a soft bristle push broom to work out any air bubbles. Immediately after brooming, roll the adhered membrane in two directions in a crossways pattern using a 100-lb (45 kg) split steel membrane roller.

REVIEW CURRENT WEATHERBOND INSTALLATION INSTRUCTIONS FOR SPECIFIC INSTALLATION REQUIREMENTS.

Precautions

1. Sunglasses that filter out ultraviolet light are strongly recommended since the membrane's white surface is highly reflective to sunlight. Roofing technicians should dress appropriately and wear sunscreen.
2. Smooth surfaces may promote slippery conditions due to frost and ice buildup. Exercise caution during cold conditions to prevent falls.
3. Care must be exercised when working close to a roof edge when the surrounding area is snow-covered, as the roof edge may not be clearly visible.
4. Use proper stacking procedures to ensure sufficient stability of the materials.
5. Exercise caution when walking on wet membrane. Membranes may be slippery when wet. the rolls until ready to use in warm, sunny weather.

Supplemental Approvals, Statements

WeatherBond FRS PVC Fleece membranes meet or exceed the requirements of ASTM D4434 Standard Specification for Poly (Vinyl Chloride) Sheet Roofing. WeatherBond FRS PVC Fleece is classified as Type III as defined by ASTM D4434.

Radiative Properties for Cool Roof Rating Council (CRRC) & LEED*

Physical Property	Test Method	White PVC	Tan PVC	Gray PVC
CRRC – Initial Solar Reflectance	ASTM C1549	0.86	0.72	0.59
CRRC – Solar Reflectance after 3 years	ASTM C1549 (uncleaned)	0.63	0.60*	0.49*
CRRC – Initial Thermal Emittance	ASTM C1371	0.89	0.87	0.89
CRRC – Thermal Emittance after 3 years	ASTM C1371 (uncleaned)	0.87	0.86*	0.86*
Solar Reflectance Index (SRI)	ASTM E1980	108	89	70
Solar Reflectance Index (SRI) after 3 years	ASTM E1980	75	65	57

LEED* Information

Pre-consumer Recycled Content	5%
Post-consumer Recycled Content	0%
Manufacturing Location	Greenville, IL
Solar Reflectance Index (SRI)	White: 108, Tan: 89, Gray: 70

Typical Properties and Characteristics

Physical Property	ASTM D4434 Requirement	115-mil	135-mil
Thickness Over Scrim, in. (mm) ASTM D4434 optical method, average of 3 areas	0.016 min (0.40)	0.030 typ. (0.762)	0.040 typ. (1.016)
Breaking Strength (MD x CD), lbf (N) ASTM D751 proc. A	200 min (890)	450 x 400	500 x 450
Elongation break of reinforcement (MD x CD), % ASTM D751 grab method	15 min	70 x 100	70 x 100
Seam Strength, min. ASTM D751 grab method (% of breaking strength)	>75	PASS	PASS
Tearing Strength (CD), lbf (N) ASTM D751 proc. B, 8 in. x 8 in.	45 (200)	60	60
Low Temperature Bend, no cracks 5x ASTM D2136	PASS	PASS (-40°C)	PASS (-40°C)
Linear Dimensional Change, % ASTM D1204, 6 hours at 176°F (MD x CD)	± 0.5 max	0.36 x 0.00 typ.	0.36 x 0.00 typ.
Ozone Resistance, no cracks 7X ASTM D1149, 100 pphm, 168 hrs	PASS	PASS	PASS
Water Absorption Resistance, mass % ASTM D570 166 hours at 158°F water	± 3.0 max.	2.0 typ.	2.0 typ.
Field Seam Strength, lbf/in. (kN/m) ASTM D1876 tested in peel	No requirement	25 (4.4) min. 60 (10.5) typ.	25 (4.4) min. 60 (10.5) typ.
Water Vapor Permeance, perms ASTM E96 proc. B	No requirement	0.10 max 0.05 typ.	0.10 max 0.05 typ.
Puncture Resistance - Dynamic, J (ft-lbf) ASTM D5635	20 (14.7)	PASS	PASS
Puncture Resistance - Static, lbf (N) ASTM D5602	33 (145)	PASS	PASS
Xenon-Arc Resistance, no cracks/ crazing 10x ASTM G155 0.35 W/m ² at 340nm, 63°C B.P.T. 12,600 kJ/m ² total radiant exposure 10,000 hours	PASS	PASS	PASS
Properties After Heat Aging ASTM D3045, 56 days at 176°F Breaking strength, % retained Elongation reinf., % retained	90 min. 90 min.	90 min. 90 min.	90 min. 90 min.

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.



WEATHERBOND
ROOFING SYSTEMS

Single-Ply Simplified

P.O. Box 251 | Plainfield, PA 17081 | 866.471.5125 | FAX: 717.960.4034 | www.weatherbondroofing.com

© 2022 WeatherBond. 08.07.22
WeatherBond is a trademark of WeatherBond. HydroBond is a trademark of Carlisle Construction Materials, LLC.
LEED is a registered trademark of the U.S. Green Building Council.