

WeatherBond

Type IV Glass Ply Felt



Overview

Type IV Glass Ply Felt is manufactured with a heavyweight fiberglass mat containing heat-cured resinous binders for added dimensional stability. The high-strength glass mat is saturated with Type IV asphalt, which provides excellent breaking strength and uniform porosity for ease of application.

Type IV Felt meets ASTM D2178 Type IV and may be used as an inner ply or base ply in a WeatherBond multi-ply system. It may be used as a base ply when mopped in place over asphalt-compatible substrates and may be used as a temporary 90-day roof when installed in a two-ply format. It can be used as a vapor retard.

Features and Benefits

- Excellent tensile strength and tear resistance
- Low moisture absorption and excellent dimensional stability
- Easy to handle and lays flat
- Non-slip surface
- Meets UL G1 base sheet requirements
- Designed for use in all climate zones

Application

Type IV Glass Ply Felt is used as a base or inner ply in conjunction with WeatherBond AC cap sheets. For non-nailable decks, Type IV can be adhered directly to the primed substrate with Type III or IV asphalt, SEBS mopping asphalt or WeatherBond's Cold Applied Adhesive. For nailable decks, G2 Base Sheet is typically mechanically fastened (using approved fasteners) to the substrate as the first ply and subsequent layers of Type IV Glass Ply Felt are mopped to the base ply. Consult WeatherBond specifications for complete installation information.

REVIEW CURRENT WEATHERBOND INSTALLATION INSTRUCTIONS FOR SPECIFIC APPLICATION REQUIREMENTS.

Specifications

1. Width – 36"
2. Length – 180'
3. Roll Weight – 47 lbs

LEED® Information

Pre-consumer Recycled Content	0%
Post-consumer Recycled Content	0%
Manufacturing Location	Tuscaloosa, AL

Typical Properties and Characteristics

Property	Value
ASTM	D2178-04 Type VI
UL	Type G1
Breaking strength, lbf/in (kN/m)	44 (7.7)
Longitude	44 (7.7) min
Transverse	
Pliability at 77°F and 50% RH; ½" radius (pass/fail)	PASS
Longitude	PASS
Transverse	
Net dry mass of saturated felt lbs/100 ft. ²	> 6.0
Net dry mass of asphalt-impregnated glass felt lbs/100 ft. ² (g/m ²)	Longitude
Average of all rolls	6.2 (303)
–nonlinearly parting agent	7.0 (342)
–mineral parting agent	6.0 (293)
Individual rolls	
Moisture, at the time of manufacturing	1.0% max
Mass of desaturated glass felt, lbs/100 ft. ²	1.7 (83) min
Asphalt, lbs/100 ft. ²	3.0 (146) min
Ash	70% to 88%
Parting agent and stabilizer, lbs/100 ft. ² (g/m ²)	3.2 (156) max

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.



WEATHERBOND
ROOFING SYSTEMS

Single-Ply Simplified

P.O. Box 251 | Plainfield, PA 17081 | 866.471.5125 | FAX: 717.960.4034 | www.weatherbondroofing.com

© 2017 WeatherBond. 11.30.17
WeatherBond is a trademark of WeatherBond. LEED is a registered trademark of the U.S. Green Building Council.